

FEP, or Fluorinated Ethylene Propylene, is a type of fluoropolymer that has become increasingly popular in recent years. FEP is a versatile material with a wide range of applications, including in the medical industry, aerospace, and even in the production of cookware.

Product Overview

Product: PF-007 has exceptional dielectric properties, low flammability is chemically inert, and has weatherability.

Typical Applications: Mainly used in aviation and aerospace industries. Subway transportation vehicles, automatic switching equipment, oil well testing equipment, flame alarm systems, high-rise buildings, near-fire area wire and cable, computers, communication networks, electrical and other fields, especially for high-speed extrusion of small-diameter wire insulation material.

Availability: It is packaged in 25-kg, single-layer, plastic bags.

TYPICAL PROPERTIES OF FEP PF-007 (Data not for specification purposes)

Properties	Test Method	Unit	PF-007
Melt Flow Rate	D2116	g/10 min	27.1–32.0
Specific Gravity	D 792		2.12–2.17
Tensile Strength, 23 °C (73 °F)	D 638	MPa	22
Elongation at Break >	D 638	%	300
Impact Strength, Notched Izod, 23 °C (73 °F)	D 256	kJ/m ²	No Break
Water Absorption	D570	%	< 0.01
Hardness, Shore Durometer	D2240	D2240	D55
Chemical Resistance	D543		Excellent
Melting Point	D 4591/ D 3418	°C (°F)	255 (591)±10
Relative Permittivity, 10 ⁶ Hz	D150		2.13
volatile matter		≤%	0.01

CERTIFICATION

-
- SGS Certification
 - ROHS Certification
 - REACH Certification
 - SVHC Certification
 - FDA Approved
 - EU Approved

PRODUCT DESCRIPTION

PF-007 is a high-performance resin that offers exceptional dielectric properties, performance at temperature extremes, low flammability, chemical inertness, weatherability, and a low coefficient of friction. It is an excellent choice for demanding applications in the chemical industry and wire and cable applications that require stress crack resistance.

PROCESSING

PF-007 resin can be processed by conventional melt extrusion, and by injection, compression, and blow molding processes. For smooth feeding to extrusion equipment, it is supplied in 3 mm (0.12 in) pellets. The extruders and molding machines used for PF-007 should be constructed of high nickel alloy corrosion-resistant materials and be capable of operating at temperatures up to 400 °C (750 °F).

STORAGE AND HANDLING

The properties of Peony FEP PF-007 resins are not affected by storage time. Ambient storage conditions should be designed to avoid airborne contamination and water condensation on the resin when opening and emptying the packaging.

ZHEJIANG V&T GROUP LIMITED

LOCATION

NO 95, Changqian Road, Kecheng
Quzhou, Zhejiang, China

CONTACT US

Phone: +86 13957007557
Email: info@peflon.com