

TECHNICAL DATA

Product: PF-303 is a melt-processible copolymer of tetrafluoroethylene and hexafluoropropylene, without additives.

Typical Applications: It is typically used for wire and cable insulation, small tubing, and injection molded parts.

Packing: 25-kg, single-layer, plastic bags.

TYPICAL PROPERTIES OF FEP PF-303 (Data not for specification purposes)

| Properties | Test Method | Unit | PF-303 |
|--|-------------|----------|------------|
| Melt Flow Rate | ASTM D2116 | g/10 min | 4.1-8.0 |
| Specific Gravity | D792 | | 2.12-2.117 |
| Critical Shear Rate | | 1/s | 22 |
| Guide DDR Range for Cable Extrusion | | | 60-120 |
| Tensile Strength, 23 °C (73 °F) ≥ | D638 | MPa | 25 |
| Elongation at Break ≥ | D638 | % | 340 |
| Impact Strength, Notched Izod, 23 °C (73 °F) | D256 | kJ/m2 | No Break |
| Hardness, Shore Durometer | D2240 | D2240 | D56 |
| Chemical Resistance | D543 | | Excellent |
| Melting Point | D4591/D3418 | °C (°F) | 260 (500) |
| Relative Permittivity, 1 GHz | D150 | | 2.15 |
| volatile matter ≤ | | % | 0.01 |

CERTIFICATION

- PFOA Free, PFAS Free
- ROHS Certification
- REACH Certification
- SVHC Certification

PROCESSING

PF-303 resin can be processed by conventional melt extrusion, and by injection, compression, and blow molding processes. For smooth feeding to extrusion equipment, it is supplied in 3 mm (0.12 in) pellets. The extruders and molding machines used for PF-303 should be constructed of high nickel alloy corrosion-resistant materials and be capable of operating at temperatures up to 400 °C (750 °F).

STORAGE AND HANDLING

The properties of FEP PF-303 resins are not affected by storage time. Ambient storage conditions should be designed to avoid airborne contamination and water condensation on the resin when opening and emptying the packaging.

QUZHOU DFS CHEM CO., LTD.

LOCATION

NO 95, Changqian Road, Kecheng Quzhou, Zhejiang, China **CONTACT US**

Phone: +86 13957007557 Email: info@peflon.com