

TECHNICAL DATA

FEP (fluorinated ethylene propylene) PF-305

Product: PF-305 is a melt-processible fluoroplastic resin available in pellet form. It is a copolymer of tetrafluoroethylene and hexafluoropropylene, without additives.

Applications: Small diameter, thin wall wire and cable insulation; industrial film; and intricate or thin wall parts made by injection molding.

Packing: It is packaged in 25-kg, single-layer, plastic bags.

TYPICAL PROPERTIES OF FEP PF-305 (Data not for specification purposes)

Properties	Test Method	Unit	PF-305
Melt Flow Rate	D2116	g/10 min	12.1-20
Specific Gravity	D 792		2.12-2.17
Tensile Strength, 23 °C (73 °F) ≥	D 638	MPa	23
Elongation at Break ≥	D 638	%	310
Impact Strength, Notched Izod, 23 °C (73 °F)	D 256	kJ/m ²	No Break
Water Absorption	D570	%	< 0.01
Hardness, Shore Durometer	D2240	D2240	D55
Chemical Resistance	D543		Excellent
Melting Point	D 4591/ D 3418	°C (°F)	257 (561)±5
Relative Permittivity, 106Hz	D150		2.15
Volatile Matter ≤		%	0.01

CERTIFICATION

- PFOA Free, PFAS Free
- ROHS Certification
- REACH Certification
- SVHC Certification

PROCESSING

PF-305 resin can be processed by conventional melt extrusion, and by injection, compression, and blow molding processes. For smooth feeding to extrusion equipment, it is supplied in 3 mm (0.12 in) pellets. The extruders and molding machines used for PF-305 should be constructed of high nickel alloy corrosion-resistant materials and be capable of operating at temperatures up to 400 °C (750 °F).

STORAGE AND HANDLING

The properties of FEP PF-305 resins are not affected by storage time. Ambient storage conditions should be designed to avoid airborne contamination and water condensation on the resin when opening and emptying the packaging.

QUZHOU DFS CHEM CO., LTD.

LOCATION

NO 95, Changqian Road, Kecheng
Quzhou, Zhejiang, China

CONTACT US

Phone: +86 13957007557
Email: info@peflon.com