

Product Overview

Product: PF-8P63 is the homopolymer of vinylidene fluoride with fine mechanical strength and toughness.

Typical Applications: It is typically used to produce PVDF products by injection, extrusion and other processing technology.

Availability: The package is packed in ton bags. The net content of ton bags is 190kg or 250kg.

TYPICAL PROPERTIES OF PVDF Powder PF-8P63 (Data not for specification purposes)

Properties	Test Method	Unit	PF-8P63
Appearance			Pellet/Powder
MFR	GB/T 3682	g/10min	14.1-25.0
Melting point	GB/T 28724	°C	165-175
Thermal decomposition,≥	GB/T 33047	°C	380
Tensile Strength,≥	GB/T 1040	Mpa	35.0
Elongation at break,≥	GB/T 1040	%	25.0
Standard relative density	GB/T 1033		1.75-1.79
Hardness	GB/T 2411	Shore D	70-80

CERTIFICATION

- SGS Certification
- ROHS Certification
- REACH Certification
- SVHC Certification

Attention

Keep PVDF Powder PF-8P63 from high temperature to prevent toxic gas releasing at the temperature above 350°C .

PACKAGE, TRANSPORTATION AND STORAGE

- 1.The package is packed in ton bags. The net content of ton bags is 155kg,190kg or 250kg.
- 2.The product should be transported as non-dangerous product, avoiding heat, moisture and strong shock.
3. Stored in clean and dry places, and temperature range is 5-30°C. Avoid contamination from dust and moisture.

QUZHOU DFS CHEM CO., LTD.

LOCATION

NO 95, Changqian Road, Kecheng
Quzhou, Zhejiang, China

CONTACT US

Phone: +86 13957007557
Email: info@peflon.com