

**Product Overview**

Product: PCTFE PF-703 has outstanding chemical stability, insulation properties, and weather resistance.

Applications: Film.

Availability: It is packed in a sealed PVC bag, and loaded in water content proof carton. Net weight (25±0.1) kg per carton.

TYPICAL PROPERTIES OF PCTFE PF-703 (Data not for specification purposes)

Properties	Test Method	Unit	PF-703
Appearance	D2116		White Powder
MFR (g/10 min) 265°C/10kg	ASTM D-792		8-12
Tensile Strength, MPa ≥	ASTM D-638	MPa ≥	50.0-85.0
Elongation at Break, % ≥	ASTM D-638	% ≥	100-150

- PCTFE PF-703 can be processed by extrusion and calendaring molding
- PCTFE PF-703 resins are not affected by storage time.
- Ambient storage conditions should be designed to avoid airborne contamination and water condensation on the resin when opening and emptying the packaging.

QUZHOU DFS CHEM CO., LTD.**LOCATION**

NO 288, Qinjiang East Road, Kecheng
Quzhou, Zhejiang, China

CONTACT US

Phone: +86 570 2969501
Email: info@peflon.com